

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 5134 (1977): Bitumen impregnated paper [CHD 15: Paper and its products]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



IS : 5134 - 1977
(Reaffirmed 2009)

Indian Standard
**SPECIFICATION FOR BITUMEN
IMPREGNATED PAPER**
(First Revision)

First Reprint FEBRUARY 1990

UDC 676.266.7

© Copyright 1978

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

AMENDMENT NO. 1 AUGUST 2004
TO
IS 5134 :1977 SPECIFICATION FOR BITUMEN
IMPREGNATED PAPER

(First Revision)

(*Page 5, clause 3.4*) — Substitute the following for the existing:

'3.4 Grammage and Tolerance on Grammage

The nominal grammage shall be as agreed to between the purchaser and the supplier. However, when tested as per 6 of IS 1060 (Part 1) : 1966*, no single test result shall vary by more than ± 6 percent from the nominal grammage. Further, the mean of 10 test results shall not vary from the nominal by more than +4 percent.'

(CHD 15)

Reprography Unit BIS, New Delhi, India

Indian Standard

SPECIFICATION FOR BITUMEN IMPREGNATED PAPER

(*First Revision*)

Paper and Pulp Based Packaging Materials Sectional
Committee, CDC 45

<i>Chairman</i>	<i>Representing</i>
SHRI S. K. KESHAHA	I. T. C. Ltd, Calcutta
<i>Members</i>	
SHRI P. DAYAL (<i>Alternate to</i> Shri S. K. Keshava)	
SHRI A. B. AJMERA	Federation of Corrugated Box Manufactures Association of India, Bombay
SHRI B. K. JOSHI (<i>Alternate</i>)	
SHRI S. P. CHATTERJEE	India Foils Ltd, Calcutta
SHRI PRABIR DAS (<i>Alternate</i>)	
SHRI RAJ K. CHAUHAN	Indian Confectionary Manufacturers Association, New Delhi
SHRI S. K. CHOPRA	Indian Paper Makers' Association, Calcutta
SHRI T. V. FRANCIS	Tata Oil Mills Co Ltd, Bombay
SHRI V. SIVARAMAN (<i>Alternate</i>)	
DR A. G. GHOSH	Ministry of Defence (R & D)
SHRI K. G. GHOSH (<i>Alternate</i>)	
SHRI PRATAP KHANNA	Federation of Biscuit Manufacturers or India, Delhi
SHRI R. D. KERAWALLA (<i>Alternate</i>)	
SHRI MAN MOHAN SINGH	Forest Research Institute and Colleges, Dehra Dun
SHRI G. M. MATHUR (<i>Alternate</i>)	
SHRI K. R. NARASIMHAN	The Metal Box Co of India Ltd, Calcutta
DR V. V. KARNIK (<i>Alternate</i>)	
SHRI P. V. NARAYANAN	Indian Institute of Packaging, Bombay
SHRI A. K. SEN GUPTA (<i>Alternate</i>)	
SHRI M. R. PARANJAPE	Indian Pharmaceutical Association, Bombay
SHRI C. Y. PATEL	Hindustan Lever Ltd, Bombay; <i>and</i> Indian Soap & Toiletries Makers Association, Bombay
SHRI P. K. BOSE (<i>Alternate</i>)	

(*Continued on page 2*)

© Copyright 1978

BUREAU OF INDIAN STANDARDS

This publication is protected under the *Indian Copyright Act* (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS : 5134 - 1977

(Continued from page 1)

Members

DR N. V. C. RAO

SHRI A. N. RAO (*Alternate*)

SHRI V. C. SOOD

SHRI G. D. GAREWAL (*Alternate*)

SHRI G. G. SUTAONE

SHRI C. V. N. RAO (*Alternate*)

DR K. K. TALWAR

SHRI S. N. KHANNA (*Alternate*)

SHRI D. V. VARMA

SHRI NIRMAL SINGH (*Alternate*)

SHRI M. L. VARMA

SHRI L. M. GUPTA (*Alternate*)

SHRI P. VEERAR???

SHRI K. R. KUMAR (*Alternate*)

DR G. M. SAXENA,
Director (Chem)

Representing

Directorate General of Technical Development,
New Delhi

Indian Tea Association, Calcutta

The Development Commissioner, Small Scale
Industries, New Delhi

Paper Products Ltd, Bombay

Ministry of Defence (DGI)

Indian Paper Mills Association, Calcutta

Central Food Technological Research Institute
(CSIR), Mysore

Director General, ISI (*Ex-officio Member*)

Secretary

SHRI SATISH CHANDER
Deputy Director (Chem), ISI

Indian Standard
**SPECIFICATION FOR BITUMEN
IMPREGNATED PAPER**
(*First Revision*)

0. FOREWORD

0.1 This Indian Standard (First Revision) was adopted by the Indian Standards Institution on 2 September 1977, after the draft finalized by the Paper and Pulp Based Packaging Materials Sectional Committee had been approved by the Chemical Division Council.

0.2 In this revision the requirement for ash has been deleted while for Cobb test has been added. On the basis of investigations done, the requirement for burst factor has been upgraded. Grade S, which was mainly meant for usage by the Ministry of Defence, has been deleted as it was found that the Ministry no longer followed this standard in their purchases. The requirements of the Defence Ministry are under consideration of the Sectional Committee and if considered possible would be included in the standard later on.

0.3 This standard contains clauses **3.3, 3.4, 3.5.1, 3.5.3** and **4.1** which call for agreement between the purchaser and the supplier and which permit the purchaser to use his option for selection to suit his requirements.

0.4 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS : 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard prescribes the requirements and the methods of sampling and test for bitumen impregnated paper intended for use as a packaging material.

*Rules for rounding off numerical values (*revised*).

IS : 5134 - 1977

2. TERMINOLOGY

2.1 For the purpose of this standard, the definitions given in IS : 4261-1967* shall apply.

3. REQUIREMENTS

3.1 General Requirements — The bitumen impregnated paper shall be a paper impregnated throughout with bitumen or pitch incorporated at the stock preparation stage in the form of an emulsion. The paper shall be of uniform formation and the surface may be glazed, unglazed or calendered as required by the purchaser. The paper shall be free from holes, lumps and other serious blemishes.

3.2 The bitumen impregnated paper shall also comply with the requirements given in Table 1 when tested according to the relevant test methods given in col 4, 5 and 6 of the table.

TABLE 1 REQUIREMENTS FOR BITUMEN IMPREGNATED PAPER

SL No.	CHARACTERISTIC	REQUIREMENT	METHOD OF TEST, REF TO CL NO. IN		
			IS : 1060 (Part I)- 1960*	IS : 1060 (Part II)- 1960†	IS : 1060 (Part III) 1969‡
(1)	(2)	(3)	(4)	(5)	(6)
	i) Burst factor, <i>Min</i> :		12.5	—	—
	Dry	12			
	Wet	6			
	ii) Moisture (as received), percent by mass, <i>Max</i>	10	9	—	—
	iii) pH	5.5 to 8.0	10	—	—
	iv) Thirty minutes Cobb test, g/m ² , <i>Max</i>	50	13.2.2	—	—
	v) Benzene soluble matter, percent by mass, <i>Min</i>	12	—	21	—
	vi) Exudation test	To pass the test	—	10	—
	vii) Water penetration test	To pass the test	—	—	10

*Methods of sampling and test for paper and allied products, Part 1 (*revised*).

†Methods of sampling and test for paper and allied products, Part II.

‡Methods of sampling and test for paper and allied products, Part III.

*Glossary of terms relating to paper and pulp-based packaging materials.

3.3 The bitumen impregnated paper may be rendered mould proof by the method agreed to between the purchaser and the supplier.

3.4 Substance and Tolerance on Substance — The substance of bitumen impregnated paper shall be as agreed to between the purchaser and the supplier. A tolerance of ± 7.5 percent of the nominal substance shall be permitted when tested according to 6 of IS : 1060 (Part I)-1966*.

3.5 Size and Tolerance on Size

3.5.1 The finished paper shall be in the form of either rolls or sheets as agreed to between the purchaser and the supplier. The sizes and tolerance on sizes shall be in accordance with IS : 1064-1961† unless otherwise agreed to between the purchaser and the supplier. The paper when in roll form shall be in continuous length of 100 metres.

3.5.2 The variation in size of paper in sheets or rolls shall not be more than 0.5 percent above or below the ordered size; where 0.5 percent is less than 3 mm, the tolerance shall be ± 3 mm and where 0.5 percent exceeds 5 mm, the tolerance shall be ± 5 mm.

3.5.3 Thickness and Tolerance on Thickness — The thickness of bitumen impregnated paper shall be as agreed to between the purchaser and the supplier. A tolerance of ± 12.5 percent shall be allowed on specified thickness.

4. PACKING AND MARKING

4.1 A ream of 500 sheets shall be the measure of quantity for bitumen impregnated paper in sheets. Packages shall contain 250 or 100 sheets according to the size and mass of the paper and packed as agreed to between the purchaser and the supplier.

4.2 Bitumen impregnated paper in rolls shall be rolled on a core of 70 mm inside diameter and in length corresponding to the width of the paper, with a wooden plug at each end extending to a minimum of 75 mm into the core.

4.3 Each package and roll shall be marked with the following information:

Package

- a) Description and substance of the paper;
- b) Contents of the package (number of sheets);

*Methods of sampling and test for paper and allied products, Part I (*revised*).

†Specification for paper sizes (*revised*).

IS : 5134 - 1977

- c) Mass in kg per ream including wrapping paper;
- d) Size in millimetres;
- e) Machine direction;
- f) Lot number;
- g) Date of manufacture; and
- h) Trade-mark, if any.

Roll

- a) Description and substance of the paper;
- b) Length and width of the roll;
- c) Mass in kg of the roll including the mass of the core and plug;
- d) Lot number;
- e) Date of manufacture; and
- f) Trade-mark, if any.

4.3.1 The material may also be marked with the ISI Certification Mark.

NOTE — The use of the ISI Certification Mark is governed by the provisions of the Indian Standards Institution (Certification Marks) Act and the Rules and Regulations made thereunder. The ISI mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well-defined system of inspection, testing and quality control which is devised and supervised by ISI and operated by the producer. ISI marked products are also continuously checked by ISI for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the ISI Certification Mark may be granted to manufacturers or processors, may be obtained from the Indian Standards Institution.

5. SAMPLING

5.1 Representative samples of packets or rolls of bitumen impregnated paper shall be selected from each lot as prescribed in **3** of IS : 1060 (Part I)-1966*.

5.2 Number of Tests

5.2.1 From each of the packets or rolls selected from the lot (*see 5.1*) one sheet shall be taken out at random. These sheets shall constitute the sample. Each one of these sheets shall first be examined for general requirements mentioned in **3.1** and one test piece shall be cut for burst

*Methods of sampling and test for paper and allied products, Part I (*revised*).

factor, exudation and water penetration test. Tests for these characteristics shall be conducted individually on each of the sample sheets. A sheet not meeting the requirements for any one or more of these characteristics shall be considered as defective.

5.2.2 For each of the remaining characteristics mentioned in 3, one test shall be made by taking the requisite number of sheets weighing approximately 100 g at random from as many of the selected packets (*see 5.1*) as possible.

5.3 Criteria for Conformity

5.3.1 A lot shall be considered as conforming to the requirements for burst factor, exudation and water penetration test if the number of defective sheets does not exceed the acceptance number. This acceptance number shall depend upon the size of the sample (*see 5.1*) and shall be equal to 0 if the sample size is less than 13. It shall be equal to 1 if the sample size is greater than or equal to 13.

5.3.2 For other characteristics which are assessed on one-test basis, the lot shall be declared as conforming to the requirements of the specification if the sheets selected for this purpose pass the test corresponding to these characteristics.

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 110002
 Telephones: 331 01 31, 331 13 75 (Common to all Offices)

Telephone

Regional Offices:

Central Manak Bhavan, 9 Bahadur Shah Zafar Marg,
 NEW DELHI 110002

*Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road,
 Maniktola, CALCUTTA 700054

Northern : SCO 445-446, Sector 35-C,
 CHANDIGARH 160036

Southern : C. I. T. Campus, MADRAS 600113

†Western : Manakalaya, E9 MIDC, Marol, Andheri (East),
 BOMBAY 400093

Branch Offices:

'Pushpak', Nurmohamed Shaikh Marg, Khanpur,
 AHMADABAD 380.001

‡Peenya Industrial Area 1 st Stage, Bangalore Tumkur Road
 BANGALORE 560058

Gangotri Complex, 5th Floor, Bhadbhada Road, T. T. Nagar,
 BHOPAL 462003

Plot No. 82/63, Lewis Road, BHUBANESHWAR 751002

53/5. Ward No. 29, R.G. Barua Road, 5th Byelane,
 GUWAHATI 781003

5-8-56C L. N. Gupta Marg (Nampally Station Road),
 HYDERABAD 500001

R14 Yudhister Marg, C Scheme, JAIPUR 302005

117/418 B Sarvodaya Nagar, KANPUR 208005

Patliputra Industrial Estate, PATNA 800013

T.C. No. 14/1421, University P.O., Palayam
 TRIVANDRUM 695035

Inspection Offices (With Sale Point):

Pushpanjali, First Floor, 205-A West High Court Road,
 Shankar Nagar Square, NAGPUR 440010

Institution of Engineers (India) Building, 1332 Shivaji Nagar,
 PUNE 411005

*Sales Office in Calcutta is at 5 Chowringhee Approach, P. O. Princep Street, Calcutta 700072

†Sales Office in Bombay is at Novelty Chambers, Grant Road, 89 66 28
 Bombay 400007

‡Sales Office in Bangalore is at Unity Building, Narasimharaja Square, 22 36 71
 Bangalore 560002

Reprography Unit, BIS, New Delhi, India